

PCT

WORLD INTELLECTUAL PROPERTY ORGANIZATION
International Bureau



INTERNATIONAL APPLICATION PUBLISHED UNDER THE PATENT COOPERATION TREATY (PCT)

(51) International Patent Classification ⁷ : C08F 255/02, C08G 81/02	A1	(11) International Publication Number: WO 00/56794 (43) International Publication Date: 28 September 2000 (28.09.00)
(21) International Application Number: PCT/EP00/02573 (22) International Filing Date: 20 March 2000 (20.03.00) (30) Priority Data: 99105661.5 19 March 1999 (19.03.99) EP (71) Applicant (for all designated States except US): FINA RESEARCH S.A. [BE/BE]; Zone Industrielle C, B-7181 Seneffe (Feluy) (BE). (72) Inventor; and (75) Inventor/Applicant (for US only): CHARLIER, Yves [BE/BE]; Chaussée de Braine-le-Comte 79, B-1400 Nivelles (BE). (74) Common Representative: FINA RESEARCH S.A.; Patent Department, Zone Industrielle C, B-7181 Seneffe (Feluy) (BE).	(81) Designated States: AE, AL, AM, AT, AU, AZ, BA, BB, BG, BR, BY, CA, CH, CN, CR, CU, CZ, DE, DK, DM, EE, ES, FI, GB, GD, GE, GH, GM, HR, HU, ID, IL, IN, IS, JP, KE, KG, KP, KR, KZ, LC, LK, LR, LS, LT, LU, LV, MA, MD, MG, MK, MN, MW, MX, NO, NZ, PL, PT, RO, RU, SD, SE, SG, SI, SK, SL, TJ, TM, TR, TT, TZ, UA, UG, US, UZ, VN, YU, ZA, ZW, ARIPO patent (GH, GM, KE, LS, MW, SD, SL, SZ, TZ, UG, ZW), Eurasian patent (AM, AZ, BY, KG, KZ, MD, RU, TJ, TM), European patent (AT, BE, CH, CY, DE, DK, ES, FI, FR, GB, GR, IE, IT, LU, MC, NL, PT, SE), OAPI patent (BF, BJ, CF, CG, CI, CM, GA, GN, GW, ML, MR, NE, SN, TD, TG). Published <i>With international search report. Before the expiration of the time limit for amending the claims and to be republished in the event of the receipt of amendments.</i>	
(54) Title: POLYPROPYLENE HAVING IMPROVED LONG CHAIN BRANCHING		
(57) Abstract Polypropylene having improved long chain branching increased melt strength obtained by irradiating polypropylene with an electron beam having an energy of at least 5 MeV and with a radiation dose of from 5 to 100 kGray in the presence of a grafting agent, the branching index of the obtained polypropylene being lower than 0.7.		

ABSTRACT

POLYPROPYLENE HAVING IMPROVED LONG CHAIN BRANCHING

Polypropylene having improved long chain branching increased melt strength obtained by irradiating polypropylene with an electron beam having an energy of at least 5 MeV and with a radiation dose of from 5 to 100 kGray in the presence of a grafting agent, the branching index of the obtained polypropylene being lower than 0.7.